

TECAMID™ 6/6 GF30

(Extruded Nylon 6/6 30% Glass-Fiber Reinforced)

TECAMID™ 6/6 GF30 is a 30% glass-fiber-reinforced nylon 6/6 material whose important properties include high tensile and flexural strength, stiffness, excellent heat deflection

temperature, and superior abrasion and wear resistance. While all TECAMID™ materials have high mechanical strength and superior resistance to wear and organic chemicals,

TECAMID™ 6/6 GF30 has more than double the strength and stiffness of unreinforced nylons and a heat deflection temperature which approaches its melting point.

- **Superior organic chemical resistance**

TECAMID™ nylons are resistant to most organic solvents.

- **High heat deflection temperature**

At 66 psi, TECAMID™ 6/6 GF30 has a HDT of 490°F. Even at 264 psi, the HDT is in excess of 480°F.

- **Excellent wear resistance**

TECAMID™ 6/6 GF30 has a wear rate approaching that of internally lubricated bearing materials. Additionally, the reinforcing glass fibers give this extruded nylon excellent abrasion and cut resistance.

- **High strength and stiffness**

TECAMID™ 6/6 GF30 has a tensile and flexural strength more than double that of unreinforced nylon and a flexural modulus three times higher. These values are equalled or exceeded only by reinforced specialty materials costing many times more.

- **Very good fatigue endurance**

TECAMID™ 6/6 GF30 has been successfully used in gears at high stress levels for many years.

- **Superior creep resistance**

TECAMID™ 6/6 GF30 has an excellent balance of properties which make it an ideal material for metal replacement in applications such as automotive parts, industrial valves, railway tie insulators, and other industry uses whose design requirements include high strength, toughness, and weight reduction.

TYPICAL PROPERTY VALUES

	PROPERTIES	ASTM Test Method	Units	TECAMID™ GF30
PHYSICAL	Density	D792	lbs/in ³	0.0488
	Specific Gravity	D792	g/cc	1.35
	Water Absorption, @24 hours, 73°F	D570	%	0.7
	@Saturation, 73°F	D570	%	5.4
MECHANICAL	Tensile Strength @ Yield, 73°F	D638	psi	12,000
	Tensile Modulus	D639	psi	400,000
	Elongation @ Break, 73°F	D638	%	10
	Flexural Strength, 73°F	D790	psi	18,500
	Flexural Modulus, 73°F	D790	psi	550,000
	Compressive Strength	D695	psi	-
	Izod Impact Strength, 73°F	D256	ft-lbs/in	1.0
	Rockwell Hardness, 73°F	D785	M Scale	90
	Shore Hardness	-	D Scale	-
	Wear Factor Against Steel, 40 psi, 50 fpm	D3702	in ³ x 1 / hr PV	-
	Static Coefficient of Friction	D3702	-	-
	Dynamic Coefficient of Friction, 40 psi, 50 fpm	D3702	-	-
THERMAL	Heat Deflection Temperature @ 66 psi	D648	°F	490
	@264 psi	D648	°F	482
	Coefficient of Linear Thermal Expansion	D696	in/in/°F	1.2 x 10 ⁻⁵
	Maximum Servicing Temperature, Intermittent	-	°F	465
	Long Term	UL746B	°F	230
	Specific Heat	-	BTU/lb-°F	-
	Thermal Conductivity	-	-	-
	Vicat Softening Point	-	°F	-
	Melting Point	D2133	°F	491
Flammability	UL94	-	-	
ELECTRICAL	Surface Resistivity	D257	ohm/square	-
	Volume Resistivity	D257	ohm-cm	-
	Dielectric Strength	D149	V/mil	-
	Dielectric Constant, @ 60 Hz, 73°F, 50% RH	D150	-	-
	@ 1 MHz	D150	-	-
	@ 20 GHz	D150	-	-
	@ 30 GHz	D150	-	-
	Dissipation Factor, @ 60 HZ, 73°F	D150	-	-

This information is only to assist and advise you on current technical knowledge and is given without obligation or liability. All trade and patent rights should be observed. All rights reserved. Data obtained from extruded shapes material. TECAMID™ – Ensinger Industries, Inc.

MATERIAL AVAILABILITY

Rods: Diameters: 3/16" to 4 3/4", 10' length
Length: 5" to 6" diameter, 5' length

Plates: 1/4" to 3" thickness inclusive are 2' x 4'
3 1/4" to 4" thickness inclusive are 1' x 2'

Primary Specification (Resin) (Typical)

ASTM-D-4066 PA011G30A00000

Shapes Specification (Typical)

ASTM-D-5989 S-PA0101G301444440

Profiles, tubes, and special sizes are custom-produced on request.



Division of Ensinger, Inc.

HEADQUARTERS
365 Meadowlands Boulevard
Washington, Pennsylvania 15301

Telephone: 800-243-3221 Sales
800-869-4029 Technical
Fax: 724-746-9209

e-mail: sales@ensinger-ind.com

DISTRIBUTED BY